

BOWSER-MORNER, INC.

Delivery Address: 4518 Taylorsville Rd • Dayton, Ohio 45424 Mailing Address: P.O. Box 51 • Dayton, Ohio 45401

AASHTO/ISO 17025 Accredited • USACE Validated



REPORT ON TESTS OF ARCHITECTURAL CAST STONE

Report To: Reading Rock, Inc.
Attn: David Zawada
4600 Devitt Drive
Cincinnati, OH 45246

Report Date: 06/07/19
Job No.: 190539
Report No.: 114691
No. of Pages: 1

Date Made: Unknown
Date(s) of Performance: 06/01/19

Date Received: 05/29/19

Test Methods: ASTM C 1194, ASTM C 1195


Specification: ASTM C 1364

Type of Unit: Rockcast Custom Cast Stone - Hand Tamp Buff

COMPRESSIVE STRENGTH - ASTM C 1194					SPECIFICATIONS	
Specimen No.	2D	2E	2F	Average	Individual	Average
Length in Inches	2.15	2.18	2.10			
Width in Inches	2.07	2.09	2.16	2.11		
Height in Inches	2.09	2.13	2.08			
Total Load in lbs.	30,525	29,880	30,970			
Gross Area, Sq. In.	4.5	4.6	4.5			
Gross Unit Load, psi	6860	6560	6830	6750	6500 Min.	6500 Min.
ABSORPTION - ASTM C 1195					SPECIFICATIONS	
Specimen No.	2A	2B	2C	Average	Individual	Average
Dry Weight, (g)	331.80	315.10	307.70			
SSD Wt., 48 HR Soak, (g)	348.50	331.20	322.70			
Absorption, 48 HR Soak, (%)	5.0	5.1	4.9	5.0	6 Max	6 Max

Should you have any questions, or if we may be of further service, please contact me at (937) 236-8805, ext. 322.

Respectfully submitted,
BOWSER-MORNER, INC.


Karl A. Fletcher, Manager
Construction Materials and
Geotechnical Laboratories

KAF/bk/jlh
114691
1-File
1-zawadad@readingrock.com