

BOWSER-MORNER, INC.

Delivery Address: 4518 Taylorsville Road Dayton, Ohio 45424 Mailing Address: P.O. Box 51 Dayton, Ohio 45401
AASHTO/ISO 17025 Accredited

REPORT ON FREEZE THAW DURABILITY

Report To: Reading Rock, Inc.
Attn: David Zawada
4600 Devitt Drive
Cincinnati, Ohio 45246

Report Date: 04/16/13
Report No.: 710121
W.O. No.: 160945
Submitted: 02/11/13

Test Method: ASTM C 666A - Resistance of Concrete to Rapid Freezing and Thawing

Specification: ASTM C 1364 - Standard Specification for Architectural Cast Stone, section 5.6


Sample ID: Capella Wet Cast

Cycle	Sample A Weight, g: 7063.5		Sample B Weight, g: 7127.9		Sample C Weight, g: 6928.1		Average % Loss @ 300 Cycles	ASTM C1364 Specification % Maximum
	Cumulative Loss, g	Loss %	Cumulative Loss, g	Loss %	Cumulative Loss, g	Loss %		
35	0.1	0.0	0.1	0.0	0.1	0.0	---	---
70	0.2	0.0	0.7	0.0	0.2	0.0	---	---
105	0.6	0.0	1.5	0.0	0.8	0.0	---	---
140	1.0	0.0	2.8	0.0	1.5	0.0	---	---
175	1.3	0.0	3.8	0.1	1.8	0.0	---	---
210	2.3	0.0	5.1	0.1	2.4	0.0	---	---
245	2.4	0.0	5.7	0.1	2.5	0.0	---	---
280	2.8	0.0	7.1	0.1	2.9	0.0	---	---
300	3.2	0.0	8.1	0.1	3.6	0.1	0.1	5.0

Should you have any questions, or if we may be of further service, please contact me at (937) 236-8805, ext. 329.

Respectfully submitted,

BOWSER-MORNER, INC.



Scott D. Ruhkamp, Supervisor
Special Projects Section
Construction Materials Laboratory
CMTT No. 5013

SDR/bk/lfg
710121
1-File
1-zawadad@readingrock.com

All Reports Remain The Confidential Property Of BOWSER-MORNER And No Publication Or Distribution Of Reports May Be Made Without Our Express Written Consent, Except As Authorized By Contract. Results Contained In This Report Are Reflective Only Of The Items Calibrated Or Tested. Unless Otherwise Agreed, Samples or Specimens Will Be Discarded Or Returned At Bowser-Morner's Discretion. AASHTO/ISO 17025 Accreditation applies only to the parameters included in BOWSER-MORNER'S current scope of accreditation. Go to www.bowser-morner.com/accreditations for review.