

BOWSER-MORNER, INC.

Delivery Address: 4518 Taylorsville Road • Dayton, Ohio 45424 Mailing Address: P. O. Box 51 • Dayton, Ohio 45401

AASHTO/ISO 17025 Accredited • USACE Validated

LABORATORY REPORT

Report To: Reading Rock, Inc.
Attn: David Zawada
4600 Devitt Drive
Cincinnati, OH 45246

Date: January 6, 2020
Report No.: 019994
W.O. No.: 192401
No. of Pages: 1

Report On: Abrasion Resistance of Concrete Interlocking Paver Units
Sample ID: Tiger Pavers


On September 30, 2019, one set of pavers were submitted for determination of abrasion resistance. Testing was performed as specified by the client and in accordance with ASTM C 418, "Abrasion Resistance of Concrete by Sand Blasting".

Results are as follows:

Hole No.	Abrasion Coefficient, cm ³ /cm ²	Abrasion Volume Loss, cm ³ /50 cm ²	ASTM C936 sec. 5.6 Specification, Max.
1	0.24	11.9	---
2	0.22	11.0	---
3	0.26	12.8	---
4	0.24	11.9	---
5	0.23	11.5	---
6	0.27	13.7	---
7	0.25	12.4	---
8	0.24	11.9	---
Ave	0.24	12.1	15 cm ³ /50 cm ²

Should you have any questions, or if we may be of further service, please contact me at (937) 236-8805, extension 329.

Respectfully submitted,
BOWSER-MORNER, INC.


Scott D Ruhkamp, Supervisor
Special Projects Section
Construction Materials Laboratory

SDR/sdr
019994
1-File
1-zawadad@readingrock.com