

BOWSER-MORNER, INC.

Delivery Address: 4518 Taylorsville Road • Dayton, Ohio 45424 Mailing Address: P. O. Box 51 • Dayton, Ohio 45401

AASHTO/ISO 17025 Accredited • USACE Validated

LABORATORY REPORT

Report To: Reading Rock, Inc.
Attn: David Zawada
4600 Devitt Drive
Cincinnati, OH 45246

Date: April 25, 2019
Report No.: 019754
W.O. No.: 189490
No. of Pages: 1

Report On: Abrasion Resistance of Concrete Interlocking Paver Units
Sample ID: 6cm Paverlock


On March 26, 2019, one set of pavers were submitted for determination of abrasion resistance. Testing was performed as specified by the client and in accordance with ASTM C 418, "Abrasion Resistance of Concrete by Sand Blasting".

Results are as follows:

Hole No.	Abrasion Coefficient, cm^3/cm^2	Abrasion Volume Loss, $\text{cm}^3/50 \text{ cm}^2$	ASTM C936 sec. 5.6 Specification, Max.
1	0.08	4.0	---
2	0.05	2.5	---
3	0.07	3.5	---
4	0.06	3.0	---
5	0.08	4.0	---
6	0.06	3.0	---
7	0.07	3.5	---
8	0.08	4.0	---
Ave	0.07	3.5	15 $\text{cm}^3/50 \text{ cm}^2$

Should you have any questions, or if we may be of further service, please contact me at (937) 236-8805, extension 329.

Respectfully submitted,
BOWSER-MORNER, INC.



Scott D Ruhkamp, Supervisor
Special Projects Section
Construction Materials Laboratory

SDR/sdr
019754
1-File
1-zawadad@readingrock.com